

ARM354X

POLYASPARTIC COATING

PRODUCT DESCRIPTION

ARM354X is a solvent based two component 80% solids polyaspartic aliphatic urethane clear coating. ARM354X has excellent chemical resistance, hardness, abrasion resistance, UV stability and has an excellent clear gardner color. However, the outstanding feature of this product is its exceptionally quick tack free time of around 1-2 hours for foot traffic.

RECOMMENDED FOR: Recommended for areas where a thin/medium build clear coat is desired over a broadcast system and installation downtime is very limited. This product is suitable as a thin/medium build coating only.

SPECS

SOLIDS BY WEIGHT	80% (+/- 3%)
SOLIDS BY VOLUME	77% (+/-3%)
VOLATILE ORGANIC CONTENT	Less than 213 grams per liter
RECOMMENDED FILM THICKNESS	2-8 mils wet
PACKAGING INFORMATION	1.5 gallon kit, 3 gallon kit (net approximately)
FINISH CHARACTERISTICS	Gloss >70 at 60 degrees
COMPRESSIVE STRENGTH	12,000 psi @ ASTM D695
TENSILE STRENGTH	3,900 psi @ ASTM D638
ULTIMATE ELONGATION	2.4%
HARDNESS	Shore D= 79
VISCOSITY	<1000 centipoise typical
DOT CLASSIFICATIONS	Part A "FLAMMABLE LIQUID N.O.S., 3, UN1993, PGIII" Part B "Not Regulated »
ABRASION RESISTANCE	Taber abraser CS-17 calibrase wheel with 1000 gram total load and 500 cycles= 21 mg loss

COVERAGE

PER GALLON	200-800 sq.ft. coverage rates will vary depending on surface porosity and texture
------------	---

COLORS

Clear - gardner color 1

CURE SCHEDULE

POT LIFE (150 g mass)	30-60 minutes (actual usable working time is approximately 5-15 minutes)
TACK FREE (Dry to touch)	1-3 hours
RECOAT OR TOPCOAT	2-4 hours
LIGHT FOOT TRAFFIC	3-5 hours
FULL CURE (heavy traffic)	24-48 hours
APPLICATION TEMPERATURE	50-90 degrees F with RH below 85%

PRIMERS

Recommend a suitable primer and testing to determine suitability

TOPCOAT

None recommended

CHEMICAL RESISTANCE

REGEANT	RATING
Xylene	C
1,1,1 trichloroethane	B
MEK	A
Methanol	B
Ethyl alcohol	B
Skydrol	C
50% sodium hydroxide	E
10% sulfuric acid	C
10% HC1 (aq)	C
5% acetic acid	C

Rating Key: Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.

FEATURES




Chemical Resistance



Quick Drying



Super Durable



UV Stable



Roll On Application

LIMITATIONS

Due to the quick cure rate and dry time, it is suggested that the user obtain a sample and thoroughly evaluate the product before using. Samples are available upon request. Color stability may be affected by environmental conditions like high humidity/chemical exposure. Exposure to some types of lighting such as sodium vapor lights may cause discolorations. Test Data based on neat resin. Clarity of color may vary from batch to batch. Substrate temperature must be 5°F above dew point. Too thick of an application may result in surface imperfections, bubble generation or product failure. Always apply a test patch to determine product suitability and adhesion performance for your proposed application method and procedures. All new concrete must be cured for at least 30 days prior to application. Do not expose this product to water until fully cured. Physical properties are typical values and not specifications. See reverse side for limitations of our liability and warranty.



ARM354X

POLYASPARTIC COATING

PRODUCT STORAGE

Store product at normal room temperature before using. Continuous storage should be between 60 and 90 degrees F.

SURFACE PREPARATION

The most suitable surface preparation would be a brush blast (shot blast) to remove all laitance and provide a suitable profile. All dirt, foreign contaminants, oil and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding.

PRODUCT MIXING

This product has a mix ratio of two parts A to one part B by volume (volumes approximate). Standard packages are in pre-measured kits and should be mixed as supplied in the kit. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. After mixing, transfer the mixed material to another pail (the transfer pail) and again remix. The material in the transfer pail is now ready to be applied on the properly prepared surface. This product has a short usable pot life of about 15 minutes which is substantially shorter than the actual gel time for the product. Applying the product beyond the usable pot life can result in surface irregularities.

PRIMING

A suitable primer should be used before applying this product. However, whether a primer is used or not, it is advisable to apply a test patch prior to using this product to determine if the adhesion characteristics are suitable for the service environment.

PRODUCT APPLICATION

The mixed material can be applied by brush or roller. Maintain temperatures and relative humidity within the recommended ranges during the application and curing process. This product is only intended for use as a thin build topcoat. Improper mixing may result in product failure. It should be pointed out that relative humidity can have a dramatic influence on the curing characteristics. The product will dry quicker and have less working time when the relative humidity is higher while a lower relative humidity will lengthen the dry time and working time.

RECOATING OR TOPCOATING

This material can be applied in multiple coats. If you opt to recoat this product, you must first be sure that the coating has tacked off before recoating. Always remember that colder temperatures will require more cure time for the product before recoating can commence.

CLEANUP

Use Xylol

FLOOR CLEANING

Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS

Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle. Dependent on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.