

ARM459X

ARMORULTRA LOW VOC CLEAR 2-PART TOPCOAT LIQUIDS ONLY

PRODUCT DESCRIPTION

ARM459X is a two component aliphatic urethane floor finish that exhibits excellent characteristics for abrasion resistance, chemical resistance, flexibility, weathering and UV stability.

RECOMMENDED FOR: auto service centers, warehouses, computer rooms, laboratories, aircraft hangers, cafeterias, and some chemical exposure areas.

SPECS

SOLIDS BY WEIGHT/VOLUME	89% / 88%
VOLATILE ORGANIC CONTENT	LESS THAN 100 G/L FOR COLORS AND LESS THAN 106 G/L FOR CLEAR
PACKAGING INFORMATION	1/4 GAL UNITS, 1 GAL UNITS, 4 GAL UNITS
SHELF LIFE	6 MONTHS IN UNOPENED CANS
MIX RATIO	1.08# PART A WITH 6.45# PART B (WEIGHTS APPROXIMATE)
FINISH	GLOSS
ABRASION RESISTANCE	TABER ABRASOR CS-17 CALIBRASE WHEEL WITH 1000 GRAM TOTAL LOAD AND 500 CYCLES = 20-25 MG LOSS
IMPACT RESISTANCE	GARDNER IMPACT = 160 IN. LB. (PASSED)
FLEXIBILITY	NO CRACKS ON A 1/8" MANDREL
ADHESION	300 PSI @ ELCOMETER ON PROPERLY PREPARED EPOXY BASECOAT
VISCOSITY	MIXED LIQUIDS A/B = 1000-2000 CPS
DOT CLASSIFICATIONS	PART A "NA1993, COMBUSTIBLE LIQUID N.O.S., 3, PG III" PART B" ENVIRONMENTALLY HAZARDOUS SUBSTANCES, LIQUID, N.O.S., UN3082, 9, PGIII,"

COVERAGE

PER GALLON	500-600 SF PER GALLON. CLEAR WILL YIELD LESS. COLORS WILL YIELD MORE
-------------------	---

COLORS

AMBER CLEAR. COLOR TINT PACKS AVAILABLE IN BLACK, BROWN, CHARCOAL, DK. GRAY, DESERT TAN, LT. BLUE, LT. GRAY, MED. GRAY, OFF WHITE, TAN, TILE RED, KHAKI TAN, WHITE

CURE SCHEDULE

POT LIFE (1 GAL)	1-2 HOURS
TACK FREE (DRY TO TOUCH)	3-6 HOURS
RECOAT OR TOPOCAT	6-10 HOURS
LIGHT FOOT TRAFFIC	14-24 HOURS
FULL CURE (HEAVY TRAFFIC)	3-5 DAYS
APPLICATION TEMPERATURE	50-90 DEGREES F WITH RELATIVE HUMIDITY BETWEEN 50-90%

PRIMERS

FOR THIN MILS SYSTEM USE ARM013X/ARM015X OR ARM 144X. FOR BUILT UP SYSTEMS USE PRIMER IN ADDITION TO ARM707X/ARM139X/ARM181X

TOPCOAT

WE DO NOT RECOMMEND MULTIPLE COATS OF THIS PRODUCT OR OTHER TOPCOATS.

CHEMICAL RESISTANCE

ACETIC ACID 5%	C
MEK	B
GASOLINE	D
50% SODIUM HYDROXIDE	D
10% SULFURIC	D
10% HYDROCHLORIC ACID	D
20% NITRIC ACID	C
ETHYLENE GLYCOL	D

Rating Key: Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion.
NOTE: extensive chemical resistance information is available through your sales representative.

FEATURES



Chemical Resistance



Super Durable



Roll On Application



Multiple Colors



Low Odor/VOC

LIMITATIONS

Color or gloss may be affected by humidity, temperatures, chemical exposure, application thickness, exposure to lighting such as sodium vapor lights. For best results use a high quality 3/8" nap roller. Slab on grade requires moisture barrier Substrate temperature must be 5°F above dew point All new concrete must be cured for at least 30 days Physical properties are typical values and not specifications Tire contact may cause staining and discoloration Colors may vary from batch to batch, therefore, use only product from the same batches for an entire job. See reverse side for application instructions. See reverse side for limitations of our liability and warranty. Do not use if relative humidity is below 35% Material has to be applied at the recommended thickness per gallon uniformly for proper appearance and development of physical properties. The epoxy basecoat must be abraded/de-glossed for proper adhesion.



ARM459X

ARMORULTRA LOW VOC CLEAR 2-PART TOPCOAT LIQUIDS ONLY

PRODUCT STORAGE: Store product at normal room temperature before using. Storage should be between 60 and 90 degree F.

SURFACE PREPARATION: Surface preparation will vary according to the type of complete system to be applied. For a one or two coat thin build system over concrete, (3-10 mils dry) we recommend either mechanical scarification or acid etching until a suitable profile is achieved. For a complete system build higher than 10 mils dry, we recommend a fine brush blast (shot blast). All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4' X 4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding. It is crucial that the epoxy basecoat is thoroughly sanded until the surface is de-glossed and appropriately and thoroughly scratched. It is recommended that a minimum 80 grit paper be used.

PRODUCT MIXING: This product has two components. The part A should be mixed with the part B thoroughly until uniform. The kits come prepackaged and should be used in their entirety and should not be broken down. If a color pack is used, it is recommended that the color pack be combined with the part A prior to adding the part B and then mixed well with the part B. After the two (or three, if color packs are used) parts are combined, mix extremely well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. Avoid whipping air into the coating. Improper mixing may result in product failure. Once the material is opened, it cannot be re-sealed for later use.

PRODUCT APPLICATION: Pour the mixed material into the application tray. Apply at the rate of 600 square feet per gallon in a uniform manner with a 3/8" nap roller. For uniform appearance, it is critical that the material is not applied thicker than this application rate. Dip the roller in the coating and roll out excess material in the roller tray prior to the actual application to the substrate. Overlap subsequent passes being sure no excess material is applied when overlapping. Make sure the floor has just enough material to cover evenly in a thin application. Finally, re-roll the area in the opposite direction of the first pass applications to level and even the application. The final re-rolling for the entire floor should be in the same direction. Remix the material in the application tray to maintain a uniform mix throughout the application process. If the appearance is not satisfactory, re-roll until the area is uniform in appearance. Maintain temperatures and humidity within the recommended ranges during the application and during the curing process. Make sure the substrate has a suitable epoxy primer that has been de-glossed (see surface preparation above) It is best to maintain a wet edge to avoid roller marks. Direct sunlight or high temperatures may cause visible roller marking during application. Too thick of an application may result in solvent entrapment and product failure. The Surface must be dry before the application of this product.

RECOAT OR TOPCOATING: Multiple coats of this product are not recommended without thoroughly evaluating the adhesion in conjunction with a thorough deglossing. If you opt to apply multiple coats of this product, a test area must be applied to test adhesion before attempting to apply multiple coats over the entire job. If you opt to recoat this product, you must first be sure that all of the solvents have evaporated from the coating during the curing process and properly de-gloss and roughen the surface (see surface preparation above). The information on the front side are reliable guidelines to follow. However, it is best to test the coating before recoating or topcoating. This can be done by pressing on the coating with your thumb to verify that no fingerprint impression is left. Always remember that colder temperatures will require more cure time for the product. Before recoating or topcoating, check the coating to insure no contaminants exist. If contaminants are present on a previous coat, remove with a standard detergent cleaner and allow to thoroughly dry. Although not recommended, when recoating this product with subsequent coats, it is advisable to apply the recoat before 24-48 hours pass only after proper surface preparation and adhesion testing has been completed.

CLEANUP: Use ketone solvents or other suitable cleaning solvent

FLOOR CLEANING: Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS: Restrict the use of the floor to light traffic, non-harsh chemicals and water until the coating is fully cured. Dependent on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

WE WARRANT THAT OUR PRODUCTS ARE MANUFACTURED TO STRICT QUALITY ASSURANCE SPECIFICATIONS AND THAT THE INFORMATION SUPPLIED BY US IS ACCURATE TO THE BEST OF OUR KNOWLEDGE. SUCH INFORMATION SUPPLIED ABOUT OUR PRODUCTS IS NOT A REPRESENTATION OR A WARRANTY. IT IS SUPPLIED ON THE CONDITION THAT YOU SHALL MAKE YOUR OWN TESTS TO DETERMINE THE SUITABILITY OF OUR PRODUCT FOR YOUR PARTICULAR PURPOSE. ANY USE OR APPLICATION OTHER THAN RECOMMENDED HEREIN IS THE SOLE RESPONSIBILITY OF THE USER. LISTED PHYSICAL PROPERTIES ARE TYPICAL AND SHOULD NOT BE CONSTRUED AS SPECIFICATIONS. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. WE SHALL HAVE NO LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES, DIRECT OR INDIRECT. OUR LIABILITY IS LIMITED TO THE NET SELLING PRICE OF OUR PRODUCT OR THE REPLACEMENT OF OUR PRODUCT, AT OUR OPTION. ACCEPTANCE OF DELIVERY OF OUR PRODUCT MEANS THAT YOU HAVE ACCEPTED THE TERMS OF THIS WARRANTY WHETHER OR NOT PURCHASE ORDERS OR OTHER DOCUMENTS STATE TERMS THAT VARY FROM THIS WARRANTY. NO REPRESENTATIVE IS AUTHORIZED TO MAKE ANY REPRESENTATION OR WARRANTY OR ASSUME ANY OTHER LIABILITY ON OUR BEHALF WITH ANY SALE OF OUR PRODUCTS. OUR PRODUCTS CONTAIN CHEMICALS THAT MAY CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.